

# SunCure® 10LM191

## Low Migration UV Curable Gloss Litho Varnish

### 1. Description

**SunCure® 10LM191** is a high performance, UV curable, low migration varnish designed for offset lithographic printing of non-food contact surfaces of primary or primary outer wrap food packaging where a risk of migration has been identified.

### 2. Product Features

- Through duct application on lithographic presses
- Good gloss and rub resistance with good slip properties
- Adhesion to a wide range of substrates including carton board and appropriately selected plastics and flexible packaging films, foils and label substrates
- Excellent taint and odour properties, with very low migration
- Manufactured only from substances listed in Annex 1 and Annex 6 of the Swiss Packaging Inks Ordinance\*
- Meets Nestlé\*\* criteria for the production of their packaging

### 3. Product Suitability

#### 3.1 Applications

SunCure® 10LM191 is intended for use in the following areas:

- Primary and primary outer wrap food packaging
- Outer wrap pharmaceutical packaging and packaging for other sensitive applications
- Appropriately selected grades of paper and board, selected flexible packaging films and a range of self-adhesive label substrates
- Subject to testing, microwave (no susceptor) and ovenable\*\*\* applications

SunCure® 10LM191 is **not** suitable for use in the following areas:

- Direct food contact

*Printers should assure themselves that use of this product on food packaging has been fully assessed for risk and that the packaging produced meets regulatory requirements for the intended end use. Whilst SunCure® 10LM191 is versatile in performance, it may not be suitable if used outside the above described applications and trials should be made before starting any commercial print run. If in doubt, please discuss suitability with your local Sun Chemical representative.*

\* Ordinance of the Federal Department of Home Affairs (FDHA) on Materials and Articles (817.023.21) Section 8b: Packaging Inks (Annex 6 revision 25.11.09)

\*\*Nestlé – “Guidance Note on Packaging Inks” 19-04-2010

\*\*\* Not exceed 200°C and not in excess of 30 minutes

#### 4.1 Safety and Handling Information

Please refer to the product Safety Data Sheet for specific information on composition, hazard properties and handling requirements.

working for you.



## Sales Specification:

Product Properties <sup>1</sup>	Test Number	Typical Values
Viscosity ( 25°C)	794	65 - 85 poise
UV Cure (Comparative)	795	As Master Standard
Static Slip <sup>2</sup>	821	0.30 – 0.50
Kinetic Slip <sup>2</sup>	821	0.20 – 0.40

## Application Data:

Print Process	Via the printing duct on a lithographic press
Film Weight <sup>3</sup>	1.0 – 2.0 gm <sup>-2</sup> , depending on requirements
Wash-Up Solvent	OEM accredited UV wash
Substrates <sup>4</sup>	Coated papers, boards and selected plastics and foils. 10LM191 is not recommended for use on substrates that are highly absorbent or have no top coating

## Compatibility:

Inks	This product is suitable for in-line or off-line printing over UV offset or UV flexo inks. It can also be used over other ink systems that are dry before application and designed to be suitable with UV coating, however trials are recommended
Hot Foil Stamping/Blocking	Unsuitable, not recommended
Gluability	Unsuitable, not recommended
Imprintability	Unsuitable, not recommended

## Notes:

<sup>1</sup> Test methods available on request

<sup>2</sup> Tested on Incada Excel board, values for guidance only. The responsibility rests with the user to establish the conditions under which the slip is considered satisfactory and subsequently monitored and controlled during printing. Slip and cure are affected by multiple factors beyond the control of Sun Chemical including press speed, UV exposure, film weight, substrate and the types and formats of the ink beneath

<sup>3</sup> The film weight recommendation is based on averaging of historical information from application equipment typically used to print this type of coating

<sup>4</sup> While this product is designed for coated paper and board, it will also work on selected plastics and foils, but trials should be undertaken before use to ensure all properties are acceptable to the customer

<sup>5</sup> 10LM191 is stable for 2 years when stored in its original container at temperatures between 5°C and 25°C, away from direct sunlight. Correctly stored material may be usable after this time but should be checked before use. Coating that is contaminated during the printing process should not be returned to the original container or properties and stability may be affected