

SunCure® 12HC171

UV Curable Gloss Coating

1. Description

SunCure® 12HC171 is a high performance, UV curable, high gloss, foil stampable coating designed for overprinting of commercial and non-food packaging printed material, and for narrow web label printing.

2. Product Features

- Medium viscosity for dry offset application on Sheetfed and Narrow Web presses
- High gloss, with good rub resistance and slip properties
- Foil stampable, with appropriately selected foils and foiling conditions
- Adhesion to a wide range of paper, board, plastic and appropriately selected synthetic substrates
- Contains benzophenone, NOT a low migration product

3. Product Suitability

3.1 Applications

SunCure® 12HC171 **is** intended for use in the following areas:

- Commercial print applications including, book, catalogue, magazine and CD/DVD covers, etc...
- Outer wrap packaging for luxury goods and non-food products
- Appropriately selected grades of paper and board and self-adhesive label substrates, check before use on foil board or plastic substrates
- ONLY suitable for use on food packaging if the packaged goods are retained within an absolute or proven functional barrier to migration, and there is no risk of migration by other means. Examples of absolute barriers include glass, metal, pouches containing a continuous layer of aluminium (>30 microns) and specially treated films and foils

SunCure® 12HC171 is **not** suitable for use in the following areas:

- Primary packaging for food, or primary outer wrap packaging for food where the goods are retained within a material that is not a barrier to migration or has unknown barrier properties
- Direct food contact,
- Applications where taint and odour are critical

Printers should assure themselves that, if 12HC171 is used on food packaging, either in-house or as a result of coating by a third party or trade finisher, the packaging has been fully assessed for risk and that the packaging so produced meets regulatory requirements for the intended end use. Whilst SunCure® 12HC171 is versatile in performance, it may not be suitable if used outside the above described applications and trials should be made before starting any commercial print run. If in doubt, please discuss suitability with your local Sun Chemical representative.

4.1 Safety and Handling Information

Please refer to the product Safety Data Sheet for specific information on composition, hazard properties and handling requirements.

working for you.



Sales Specification:

Product Properties ¹	Test Number	Typical Values
Comparative Gloss	817	As Master Standard
Viscosity (Brookfield 25°C)	799	35.0 – 50.0 poise
UV Cure (Comparative)	795	As Master Standard
Static Slip ²	821	0.25 – 0.35
Kinetic Slip ²	821	0.20 – 0.30

Application Data:

Print Process	Anilox coater or roller coating device, stir before use
Film Weight ³	2.0 to 4.0 g/m ² , depending on requirements
Wash-Up Solvent	OEM accredited UV wash
Substrates ⁴	Coated papers, boards and appropriately selected synthetic substrates. Test before use on plastics or substrates that are highly absorbent or have no top coating

Compatibility:

Inks	This product is suitable for in-line or off-line printing over UV offset or UV flexo inks. It can also be used over other ink systems that are dry before application and designed to be suitable with UV coating, however trials are recommended
Hot Foil Stamping/Blocking	With care, check in conditions of use before proceeding
Glueability	With care, check in conditions of use before proceeding
Imprintability	With care, check in conditions of use before proceeding

Notes:

¹ Test methods available on request

² Tested on Incada Excel board, values for guidance only. The responsibility rests with the user to establish the conditions under which the slip is considered satisfactory and subsequently monitored and controlled during printing. Slip, cure and surface energy are affected by multiple factors beyond the control of Sun Chemical including press speed, UV exposure, film weight, substrate and the types and formats of the ink beneath

³ The film weight recommendation is based on averaging of historical information from application equipment typically used to print this type of coating

⁴ While this product is designed for coated paper and board, it will also work on selected plastics and foils, but trials should be undertaken before use to ensure all properties are acceptable to the customer

⁵ 12HC171 is stable for 2 years when stored in its original container at temperatures between 5°C and 25°C, away from direct sunlight. Correctly stored material may be usable after this time but should be checked before use. Coating that is contaminated during the printing process should not be returned to the original container or properties and stability may be affected